



Do Moss Grd



3. Results of inspection :

1) American National Standard ANSI Z80.3-2001 : Clause 4.6-Transmittance Properties


Inspection item		No. Do-Moss Grd	Judgment (General purpose)
Luminous transmittance τ_v		11.9 %	Pass
Mean transmittance	UVB(290-315nm)	0.0 % (0.000 τ_v)	Pass
	UVA(315-380nm)	0.0 % (0.000 τ_v)	Pass
Color limits	Yellow traffic signal	X 0.59 Y 0.41	Pass
	Green traffic signal	X 0.23 Y 0.49	Pass
	Average daylight (D65)	X 0.38 Y 0.41	Pass
Traffic signal transmittance	Red signal	16.7 %	Pass
	Yellow signal	13.2 %	Pass
	Green signal	11.2 %	Pass
Spectral transmittance(500-650nm)		10.2 % (0.857 τ_v)	Pass

2) European Standard EN 1836-2005 : Clause 4.1.3.2-Requirements for road use and driving

Inspection item	No. Do-Moss Grd	Judgment
τ_v (D ₆₅)	11.9 %	Pass
Filter category	—	3
τ_F (280-315nm) MAX	0.0 % (0.000 τ_v)	Pass
τ_F (315-350nm) MAX	0.0 % (0.000 τ_v)	Pass
$\tau_{SUV A}$ (315-380nm)	0.0 % (0.000 τ_v)	Pass
τ_F (500-650nm) MIN	10.2 % (0.857 τ_v)	Pass
Red signal light Q	15.0 % (1.261 τ_v)	Pass
Yellow signal light Q	13.3 % (1.118 τ_v)	Pass
Green signal light Q	11.2 % (0.941 τ_v)	Pass
Blue signal light Q	12.1 % (1.017 τ_v)	Pass

3) Australian/New Zealand Standard AS/NZS 1067-2003 :
Clause 2.1-Transmittance requirements and lens categories

Inspection item	No. Do-Moss Grd	Judgment
τ_v (D ₆₅)	11.9 %	Pass
Lens category	—	3
τ_F (280-315nm) MAX	0.0 % (0.000 τ_v)	Pass
τ_F (315-350nm) MAX	0.0 % (0.000 τ_v)	Pass
$\tau_{SUV A}$ (315-400nm)	0.0 % (0.000 τ_v)	Pass
τ_F (450-650nm) MIN	4.4 % (0.370 τ_v)	Pass
Red signal light Q	15.0 % (1.261 τ_v)	Pass
Yellow signal light Q	13.3 % (1.118 τ_v)	Pass
Green signal light Q	11.2 % (0.941 τ_v)	Pass
Blue signal light Q	12.1 % (1.017 τ_v)	Pass



DO-MOSSG ———

Applicant : INUI LENS CO., LTD.

Sample : Uncut plastic polarized sunglass lens only. No. Do Moss Grd
(ϕ 72mm x t 2.2mm x 6R)

Date : Feb. 19, 2008

Measuring Instrument : Spectrophotometer UV-3100PC (Shimadzu Corporation)